

IN THE CLAIMS

This listing of claims replaces all prior versions and listings of the claims in the above-referenced application.

1. (Original) A light emitting device comprising:  
a light emitting diode;  
a submount;  
a phosphor material disposed around at least a portion of said light emitting diode; and  
an underfill between a first surface of the light emitting diode and a first surface of the submount, wherein the underfill has characteristics to reduce contamination of the light emitting diode by the phosphor material.
2. (Original) The light emitting device of claim 1, wherein the light emitting diode has a reflective layer.
3. (Original) The light emitting device of claim 2, wherein the reflective layer comprises silver.
4. (Original) The light emitting device of claim 1, wherein the submount comprises a silicon substrate.
5. (Original) The light emitting device of claim 1, wherein the phosphor material comprises a material selected from a group consisting of strontium thiogallate, calcium thiogallate, strontium sulfide, and any combination thereof.
6. (Original) The light emitting device of claim 1, wherein the phosphor material comprises a sulfur compound.
7. (Currently Amended) The light emitting device of claim 1, wherein the phosphor material is included in a phosphor formulation, the phosphor formulation further [comprises] comprising a gettering compound, the gettering compound comprising a gettering ion and a counter-ion, said gettering ion comprising a material selected from a group

PATENT LAW  
GROUP LLP  
2631 N. FIRST ST.  
SUITE 223  
SAN JOSE, CA 95134  
(408) 582-0480  
FAX (408) 582-0481

consisting of Group VA elements, Group VB elements, Group VIB elements, Group IVA elements, organic ligands, and any combination thereof.

8. (Original) The light emitting device of claim 1, wherein the underfill comprises a material selected from a group consisting of cyanate ester resin, epoxy resin, epoxy, urethane, acrylate, and any combination thereof.

9. (Original) The light emitting device of claim 1, wherein the underfill comprises a filler.

10. (Original) The light emitting device of claim 9, wherein the filler comprises a material selected from a group consisting of silicon dioxide, fumed silica, titanium dioxide, inorganic silicates, inorganic clays, inert metals, metal oxides, and any combination thereof

11. (Original) The light emitting device of claim 9, wherein the filler is reflective.

12. (Original) The light emitting device of claim 1, wherein the underfill comprises a gettering compound, the gettering compound comprising a gettering ion and a counter-ion, said gettering ion comprising a material selected from a group consisting of Group VA elements, Group VB elements, Group VIB elements, Group WA elements, organic ligands, and any combination thereof.

13. (Original) The light emitting device of claim 12, wherein the underfill further comprises fumed silica.

14. (Original) The light emitting device of claim 12, wherein the gettering ion comprises a material selected from a group consisting of chromium, molybdenum, tungsten, vanadium, niobium, tantalum, bismuth, hafnium, lead, and any combination thereof.

15. (Original) The light emitting device of claim 12, wherein the gettering ion and a sulfide ion form a compound with a solubility product less than about  $10^{-30}$ .

16-21. (Withdrawn).

22. (New) The light emitting device of claim 12, wherein the counter-ion is one of

PATENT LAW  
GROUP LLP  
2635 N. FIRST ST.  
SUITE 220  
SAN JOSE, CA 95134  
(408) 382-0480  
FAX (408) 382-0481

sulfate and citrate.

23. (New) The light emitting device of claim 7, wherein the gettering compound comprises about one to about ten weight percent of the phosphor formulation.

24. (New) The light emitting device of claim 1, wherein the light emitting diode is mounted on the submount.

25. (New) The light emitting device of claim 1, further comprising a coating comprising a gettering compound, the gettering compound comprising a gettering ion and a counter-ion, the coating being disposed between the light emitting diode and the phosphor material.

26. (New) The light emitting device of claim 25 wherein the coating comprises a carrier selected from the group of two part curable silicon, epoxy, and acrylic.

27. (New) A structure comprising:

a semiconductor light emitting device;

a submount;

a material containing a phosphor disposed around at least a portion of semiconductor light emitting device; and

an underfill disposed in at least a portion of a space between the semiconductor light emitting diode and the submount such that the underfill forms a physical barrier that prevents the phosphor-containing material from occupying the space.

28. (New) The structure of claim 27, wherein the underfill comprises a material selected from a group consisting of cyanate ester resin, epoxy resin, epoxy, urethane, acrylate, and any combination thereof.

29. (New) The structure of claim 27, wherein the underfill comprises a filler.

30. (New) The structure of claim 29, wherein the filler comprises a material selected from a group consisting of silicon dioxide, fumed silica, titanium dioxide, inorganic

PATENT LAW  
GROUP LLP  
2035 N. FIRST ST.  
SUITE 220  
SAN JOSE, CA 95134  
(408) 382-0480  
FAX (408) 382-0481

silicates, inorganic clays, inert metals, metal oxides, and any combination thereof

31. (New) The structure of claim 29, wherein the filler is reflective.

32. (New) The structure of claim 27, wherein the underfill comprises a gettering compound, the gettering compound comprising a gettering ion and a counter-ion.

33. (New) The structure of claim 27 wherein the underfill completely fills the space between the semiconductor light emitting device and the submount.

34. (New) A structure comprising:

a semiconductor light emitting device;

a material containing a phosphor disposed around at least a portion of semiconductor light emitting device; and

a gettering compound comprising a gettering ion and a counter-ion, the gettering compound positioned to prevent the phosphor-containing material from contaminating the semiconductor light emitting device.

35. (New) The structure of claim 34 wherein the gettering compound is included in a coating disposed between the phosphor-containing material and the semiconductor light emitting device.

36. (New) The structure of claim 34 wherein the gettering compound is included in the material.

37. (New) The structure of claim 34 wherein the semiconductor light emitting device is mounted on a submount, and the gettering compound is included in an underfill disposed between the semiconductor light emitting device and the submount.

38. (New) The structure of claim 34 wherein the gettering ion comprises a material selected from a group consisting of Group VA elements, Group VB elements, Group VIB elements, Group IVA elements, organic ligands, and any combination thereof.

39. (New) The structure of claim 34, wherein the counter-ion is one of sulfate and

citrate.

40. (New) The structure of claim 34, wherein the semiconductor light emitting device includes a contact comprising silver.

41. (New) The structure of claim 34, wherein the phosphor comprises a material selected from a group consisting of strontium thiogallate, calcium thiogallate, strontium sulfide, and any combination thereof.

42. (New) The structure of claim 34, wherein the phosphor comprises a sulfur compound.

43. (New) The structure of claim 34, wherein the gettering ion comprises a material selected from a group consisting of chromium, molybdenum, tungsten, vanadium, niobium, tantalum, bismuth, hafnium, lead, and any combination thereof.

44. (New) The structure of claim 34, wherein the phosphor comprises a sulfide ion, and wherein the gettering ion and the sulfide ion form a compound with a solubility product less than about  $10^{-30}$ .

PATENT LAW  
GROUP LLP  
2633 N. FIRST ST.  
SUITE 203  
SAN JOSE, CA 95134  
(408) 382-0481  
FAX (408) 382-0481